



822 Huber Road
Macon, GA 31217

Phone: 478 750 - 5410
Fax: 478 745 - 1116

www.kaminllc.com

HYDRAPRINT[®] Kaolin Clay

HYDRAPRINT[®] is standard particle size distribution delaminated coating clay especially suited for LWC and merchant grades where printing smoothness and coverage are of primary importance.

Typical Physical Properties

Physical Form.....	Spray Dried, Slurry
TAPPI Brightness, %	87.5 – 89.0
Screen Residue, 325 mesh, (max.), %	0.005
Moisture, (max.) %	1.5
pH, (28% solids).....	6.0 – 8.0
Brookfield Viscosity (max.), 20 rpm, 25° C, cps	450
Slurry Solids, %	67.0 - 69.0
Shipping Point	Macon/Sandersville, GA

The above data are representative data for this product and should not be perceived as specifications or maximum/minimum values.

The information contained herein is believed to be accurate and reliable, but **KaMin MAKES NO WARRANTIES OR MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, OR ANY OTHER EXPRESS OR IMPLIED WARRANTY.** The information herein relates only to the specific product described and not to such product in combination with any other product. Providing information as herein contained is not to be regarded by implication or otherwise as conveying any rights or permission for use which would violate any patent rights, property rights or violate any law, safety code or insurance regulation. Natural mineral products are subject to the normal variations related to the deposits from which they are mined.