



822 Huber Road
Macon, GA 31217

Phone: 478 750 - 5410
Fax: 478 745 - 1116

www.kaminllc.com

KaMinTex™ Kaolin Clay

KaMinTex™ is a high brightness calcined clay for filler and paper coating applications.

Typical Physical Properties

Physical Form	Dry
TAPPI Brightness.....	92.0 – 93.5
ISO Brightness.....	90.0 – 92.0
Particle Size Distribution, % finer than 2μ.....	NA
Screen Residue, (max., % > 44μ).....	0.01
Moisture, (max.as produce) %	1.0
pH, (28% solids).....	5.5 – 7.0
Brookfield Viscosity (max. at 50% solids, 20 rpm, 25° C) mPas.....	NA
Shipping Point	Macon/Sandersville/Wrens, GA

The above data are representative data for this product and should not be perceived as specifications or maximum/minimum values.

The information contained herein is believed to be accurate and reliable, but **KaMin MAKES NO WARRANTIES OR MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, OR ANY OTHER EXPRESS OR IMPLIED WARRANTY.** The information herein relates only to the specific product described and not to such product in combination with any other product. Providing information as herein contained is not to be regarded by implication or otherwise as conveying any rights or permission for use which would violate any patent rights, property rights or violate any law, safety code or insurance regulation. Natural mineral products are subject to the normal variations related to the deposits from which they are mined.